

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
14 March 2002 (14.03.2002)

PCT

(10) International Publication Number
WO 02/20644 A2

(51) International Patent Classification⁷: **C08G 81/00**

(21) International Application Number: PCT/EP01/10444

(22) International Filing Date:
10 September 2001 (10.09.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/231,902 11 September 2000 (11.09.2000) US

(71) Applicant (for all designated States except US): **UNIVERSITE DE LIEGE** [BE/BE]; ANTHEUNIS, Nicole, Quai Van Beneden 25, B-4020 Liège (BE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BAIDAK, Alexandre** [—/BE]; Place de Bronckart 2, B-4000 Liege (BE). **BRASSINE, Christine** [BE/BE]; Rue du Maupassage 20, B-6723 Habay-La-Vieille (BE). **LIEGEOIS, Jean-Marie** [BE/BE]; Moulin de Wadeleux, 411, B-4654 Charneuxus (BE). **OUHADI, Trazollah** [BE/BE]; Quai Gloesener 5, B-4000 Liege (BE).

(74) Agent: **UNIVERSITE DE LIEGE**; Antheunis, Nicole, Quai Van Beneden, 25, B-4020 Liege (BE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian

patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

— of inventorship (Rule 4.17(iv)) for US only

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: UNIVERSAL COMPATIBILIZING AGENT FOR POLYOLEFINES AND POLAR PLASTICS

(57) Abstract: Product, method and use of a copolymer AB as a compatibilizing agent between a polar thermoplastic polymer C and a polyolefine D. The method of making AB comprise the steps of: a) melting a copolymer (A) comprising a larger amount of methylmethacrylate units and a smaller amount of functional vinyl or (meth)acrylate units wherein functional moiety is selected in the group consisting of (a hydroxyl, a carboxylic, a glycidyl or an amine functional group); together with maleic anhydride grafted polypropylene (B) allowing condensation reaction to occur between the functions under "A" and the anhydride under "B"; b) the condensation copolymer obtained under a) is further melt together with the two polymers C and D to be homogenized, or melt processed as an interlayer between the two molten polymers.



WO 02/20644 A2

Universal compatibilizing agents for polyolefines and polar plastics

Promoting the adhesion between two immiscible polymers has been a concern of increasing interest. Most useful applications are polymer alloying in very fine dispersion of one polymer into the other, and laminated structures and profiles obtained by coextrusion or colamination for example.

Various solutions have been proposed to induce some degree of interfacial bonding between two polymers exhibiting no or poor mutual adhesion. Among others, a favorite route is interleaving a third polymeric component whose segments provide good spontaneous adhesion with either component respectively. Master examples are di-block copolymers made by anionic polyaddition [references: S. H. Anastasiadis, I. Gancarz and J. T. Koberstein, *Macromolecules* **1989**, 22, 1449-1453; C. Creton, E. J. Kramer, C.-Y. Hui and H. R. Brown, *Macromolecules* **1992**, 25, 3075-3088]. Unfortunately, none of the existing commercial block copolymers is suitable to provide enough bonding strength between a polyolefine D such as polypropylene and a polar polymer C such as polyvinyl halide, polyvinylidene halide, poly(meth)acrylate, polyester, or polycarbonate.

It has been found surprisingly that a suitable compatibilizing agent AB of binary or ternary mixtures comprising at least one compound of the two above cited series of polymers C and D, can be obtained by the following way :

i. A copolymer (A) comprising a larger amount of methylmethacrylate units and a smaller amount of functional vinyl or (meth)acrylate units wherein the functional moiety is characterized as being a hydroxyl, a carboxylic, a glycidyl or an amine functional group.

ii. The copolymer A described under "i" is melt processed together with maleic anhydride grafted polypropylene (B) allowing condensation reaction to occur between the functions under "i" and the anhydride under "ii".

iii. The new segmented multiblock copolymer obtained under "ii", is further melt processed together with the two polymers C and D to be homogenized, or melt processed as an interlayer between the two molten polymers.

5

Accordingly, the present invention provides a method of making a copolymer AB as a compatibilizing agent between a polar thermoplastic polymer C and a polyolefine D comprising the steps of:

- 10 a) melting a copolymer (A) comprising a larger amount of methylmethacrylate units and a smaller amount of functional vinyl or (meth)acrylate units wherein functional moiety is selected in the group consisting of (a hydroxyl, a carboxylic, a glycidyl or an amine functional group);
- together with maleic anhydride grafted polypropylene (B) allowing condensation reaction to occur between the functions under "A" and the anhydride under "B";
- 15 b) the condensation copolymer obtained under a) is further melt together with the two polymers C and D to be homogenized, or melt processed as an interlayer between the two molten polymers.

20 In a preferred embodiment of the invention, the copolymer A contains 0.02 to 6 (x) mole percent of structural units bearing the functional group, the grafted copolymer B contains from 0.2 to 3 (y) mole percent of maleic anhydride units, the ratio of copolymer A and grafted copolymer B in the multiblock copolymer AB is such that the ratio x over y lies between 10 and 1 and preferably between 6 and 2.

25 In another preferred embodiment of the invention, the copolymer A contains between 0.1 to 6 mole percent of 2-hydroxyethyl(meth)acrylate and its weight average molecular weight (measured as PS equivalent molecular weight) is between 40000 and 500000 g/mol, preferably between 150000 and 500000 g/mol.

30 The copolymer A is easily obtained for example by solution polymerization in a suitable solvent such as methylethylketone (MEK), using a thermal initiator.

The present invention also provides a use of copolymer AB as defined above as a compatibilizing agent between a polar thermoplastic polymer C like polyvinyl halide homo or copolymer, polyvinylidene halide homo or copolymer, poly(meth)acrylate, polyester, or polycarbonate and a polyolefine D as single polymer or in blend with other polyolefines.

Polyolefine D can be polypropylene homo or copolymer with one of more co-monomer and made either with Ziegler-Natta catalyzer or with single site catalyzer. Polypropylene copolymer can have random or multisequence structure including the reactor made copolymer known as block copolymer.

Polyolefine D can also be a homo polyethylene or a co-polyethylene with zero to 50 wt % of a co-monomer with a number of carbon atoms from 3 to 20.

Endly polyolefine D can be a blend of a polymer D defined above with a polyolefinic rubber like EPDM, butyl rubber, BR, SBR.

Maleic anhydride grafted polypropylene is available in various grades and can be supplied by DuPont under the trademark FUSABOND®, by Exxon under the trademark EXXELOR®, by Uniroyal under the trademark POLYBOND®, by Atofina under the trademark OREVAC™ for example.

Example 1:

In a 2 liter stirred reactor, 840 g of methylethylketone, 274 g of methylmethacrylate, 6 g of 2-hydroxyethylmethacrylate (HEMA) and 2.8 g of azobis(isobutyronitrile) are introduced. The oxygen is removed by flushing dry nitrogen in the solution. The temperature is raised to 66 °C. The solution is reacted over 24 hours at 66 °C. An additional 1.4 g of azobis(isobutyronitrile) is added to the solution and the reaction is carried on during 12 more hours. The

copolymer is recovered by precipitation of the solution in deionized water as non solvent and then dried. The yield obtained is 95 % for the methylmethacrylate and 100 % for the HEMA. The copolymer is characterized
5 by weight average molecular weight of 152000 g/mol as measured by gel permeation chromatography.

The reactive melt processing leading to the copolymer AB is carried on by mixing 200 g of copolymer A, as prepared following the above description, and
10 100 g of copolymer B, FUSABOND® MD-353D, on a two roll mill at 180 °C during 30 minutes.

Sandwich elements consisting of a polypropylene sheet (1 mm thick) and a polyvinylidene fluoride sheet (2 mm thick) are bonded with a thin film (100
15 microns thick) of copolymer AB. The sandwiches are bonded by pressing the above construction during 15 minutes at 150 °C. The adhesion between the two sheets is tested by means of a U-peel test (reference: S. Wu, *Polymer interface and adhesion*, M. Dekker Inc., New York, 1982). A fracture energy (G) of 1607 J/m² has been measured.

20

Examples 2 to 5:

In the example 2 to 4, the same experimental procedure as described in the example 1 has been followed. The HEMA amount introduced in the copolymer A is varied (see the following table) as well as the weight average molecular
25 weight, by means of a transfer agent (dodecanethiol-DDT). The measured fracture energies (G) are given for each example.

30

5

Example number	mol % HEMA in		copolymer A		wt % DDT ^a	Mw
(g/mol) of copolymer A	x/y		G (J/m ²)			
2	1.68	0.49	94000	2.3	1036	
3	1.76	0.17	222000	2.4	1513	
5	4	5.09	0	172000	5.4	1659
5:without copolymer	-	-	-	-	63	

^a: This percentage is relative to the initial total mass of monomers used in the synthesis of copolymer A.

10 Example 6:

The blending of polyvinylidene fluoride with polypropylene is evaluated with and without using the copolymer AB. In particular, the blend of 19 weight percent of polyvinylidene fluoride, 76 weight percent of polypropylene and 5 weight percent of a copolymer AB (copolymer number 5 in the table presented above) prepared on a two roll mill (roll diameter: 110 mm; temperature: 180 °C; roll speed: 15 rpm; gap: 1 mm) leads to a two phase material presenting particles whose diameter ranges between 3 and 10 μm whereas the blending of polyvinylidene fluoride and polypropylene without copolymer displays particles characterized by a larger diameter, between 15 and 80 μm .

CLAIMS

1. Method of making a copolymer AB as a compatibilizing agent between a polar thermoplastic polymer C and a polyolefine D comprising the steps of:
- 5 a) melting a copolymer (A) comprising a larger amount of methylmethacrylate units and a smaller amount of functional vinyl or (meth)acrylate units wherein functional moiety is selected in the group consisting of (a hydroxyl, a carboxylic, a glycidyl or an amine functional group);
- together with maleic anhydride grafted polypropylene (B) allowing condensation
- 10 reaction to occur between the functions under "A" and the anhydride under "B";
- b) the condensation copolymer obtained under a) is further melt together with the two polymers C and D to be homogenized, or melt processed as an interlayer between the two molten polymers.
- 15
2. Method according to claim 1 wherein the copolymer (A) contains 0.02 to 6 (x) mole percent of structural units bearing the functional group, the grafted copolymer (B) contains from 0.2 to 3 (y) mole percent of maleic anhydride units, the ratio of copolymer A and grafted copolymer B in the multiblock copolymer
- 20 AB is such that the ratio x over y lies between 10 and 1 and preferably between 6 and 2.
3. Method according to claim 2 wherein the copolymer (A) contains between 0.1 to 6 mole percent of 2-hydroxyethyl(meth)acrylate and its weight average
- 25 molecular weight is between 40000 and 500000 g/mol, preferably between 150000 and 500000 g/mol.
4. Use of copolymer AB obtained by the method according to claim 1 to 3 as a compatibilizing agent between a polar thermoplastic polymer C and a
- 30 polyolefine D .

5. Use of copolymer AB according to claim 4 wherein the Polyolefine D is a polypropylene homo or a copolymer with one of more co-monomer.
- 5 6. Use of copolymer AB according to claim 4 wherein the Polyolefine D is a homo polyethylene or a co-polyethylene with zero to 50 wt % a co-monomer with a number of carbons from 3 to 20.
- 10 7. Use of copolymer AB according to anyone of claim 4 to 6 wherein the Polyolefine D is a blend with a polyolefinic rubber.
8. Use of copolymer AB according to Claim 7 with a rubber phase partially or fully crosslinked.
- 15 9. Use of copolymer AB according to Claims 4 to 8 with additive like inorganic filler and well known polymer stabilizers.
10. Copolymer AB obtained by the method according to anyone of claim 1 to 3

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
14 March 2002 (14.03.2002)

PCT

(10) International Publication Number
WO 02/20644 A3(51) International Patent Classification⁷: **C08G 81/02**,
C08L 23/10CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD,
TG).

(21) International Application Number: PCT/EP01/10444

Declarations under Rule 4.17:

(22) International Filing Date:

10 September 2001 (10.09.2001)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

60/231,902

11 September 2000 (11.09.2000) US

(71) Applicant (for all designated States except US): **UNIVERSITE DE LIEGE** [BE/BE]; ANTHEUNIS, Nicole, Quai Van Beneden 25, B-4020 Liège (BE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BAIDAK, Alexandre** [BE/GB]; 19, Lime Road, Guisborough, TS14 6JL (GB). **BRASSINE, Christine** [BE/BE]; Rue du Mau-passage 20, B-6723 Habay-La-Vieille (BE). **LIEGEOIS, Jean-Marie** [BE/BE]; Moulin de Wadeux, 411, B-4654 Charneux (BE). **OUHADI, Trazollah** [BE/BE]; Quai Gloesener 5, B-4000 Liège (BE).(74) Agent: **UNIVERSITE DE LIEGE**; Anthéunis, Nicole, Quai Van Beneden, 25, B-4020 Liège (BE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,

as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

of inventorship (Rule 4.17(iv)) for US only

Published:

with international search report

before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:

2 May 2002

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: UNIVERSAL COMPATIBILIZING AGENT FOR POLYOLEFINES AND POLAR PLASTICS

(57) **Abstract:** Product, method and use of a copolymer AB as a compatibilizing agent between a polar thermoplastic polymer C and a polyolefine D. The method of making AB comprise the steps of: a) melting a copolymer (A) comprising a larger amount of methylmethacrylate units and a smaller amount of functional vinyl or (meth)acrylate units wherein functional moiety is selected in the group consisting of (a hydroxyl, a carboxylic, a glycidyl or an amine functional group); together with maleic anhydride grafted polypropylene (B) allowing condensation reaction to occur between the functions under "A" and the anhydride under "B"; b) the condensation copolymer obtained under a) is further melt together with the two polymers C and D to be homogenized, or melt processed as an interlayer between the two molten polymers.



WO 02/20644 A3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/10444

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08G81/02 C08L23/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G C08L C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, PAJ, EPO-Internal, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Section Ch, Week 199405 Derwent Publications Ltd., London, GB; Class A17, AN 1994-040099 XP002190638 & JP 05 345868 A (KURARAY CO LTD), 27 December 1993 (1993-12-27)	1,10
Y	abstract	1-10
Y	--- "MODIFICATION OF POLYAMIDE BY A CRYSTALLINE POLYOLEFIN AND GRAFT COPOLYMER" RESEARCH DISCLOSURE, KENNETH MASON PUBLICATIONS, HAMPSHIRE, GB, no. 332, 1 December 1991 (1991-12-01), pages 913-917, XP000274621 ISSN: 0374-4353 the whole document --- -/--	1-10

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

18 February 2002

Date of mailing of the international search report

11/03/2002

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Niaounakis, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/10444

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>DATABASE WPI Section Ch, Week 198601 Derwent Publications Ltd., London, GB; Class A17, AN 1986-004879 XP002190639 & JP 60 233131 A (MITSUI TOATSU CHEM INC), 19 November 1985 (1985-11-19) abstract</p> <p style="text-align: center;">---</p>	1, 10
A	<p>"POLYPROPYLENE/POLAR POLYMER BLENDS" RESEARCH DISCLOSURE, KENNETH MASON PUBLICATIONS, HAMPSHIRE, GB, no. 330, 1 October 1991 (1991-10-01), pages 726-734, XP000264983 ISSN: 0374-4353 the whole document</p> <p style="text-align: center;">---</p>	1
A	<p>EP 0 335 649 A (ROHM & HAAS) 4 October 1989 (1989-10-04) claim 1</p> <p style="text-align: center;">---</p>	1
A	<p>DATABASE WPI Section Ch, Week 199051 Derwent Publications Ltd., London, GB; Class A17, AN 1990-380881 XP002190640 & JP 02 276841 A (OJI YUKA GOSEISHI KK), 13 November 1990 (1990-11-13) abstract</p> <p style="text-align: center;">---</p>	1
A	<p>DATABASE WPI Section Ch, Week 199211 Derwent Publications Ltd., London, GB; Class A14, AN 1992-085310 XP002190641 & JP 04 028743 A (SUMITOMO CHEM CO LTD), 31 January 1992 (1992-01-31) abstract</p> <p style="text-align: center;">-----</p>	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/10444

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 5345868	A	27-12-1993	NONE
JP 60233131	A	19-11-1985	NONE
EP 0335649	A	04-10-1989	DK 552689 A 06-11-1989
		US 4957974 A 18-09-1990	
		AT 141933 T 15-09-1996	
		AU 3171689 A 05-10-1989	
		BE 1003120 A5 03-12-1991	
		CN 1041765 A 02-05-1990	
		CN 1092782 A 28-09-1994	
		DE 3910062 A1 26-10-1989	
		DE 68927018 D1 02-10-1996	
		DE 68927018 T2 20-03-1997	
		DK 149389 A 30-09-1989	
		EP 0335649 A2 04-10-1989	
		FI 891479 A 30-09-1989	
		FR 2629462 A1 06-10-1989	
		GB 2216892 A ,B 18-10-1989	
		JP 2261811 A 24-10-1990	
		JP 2022316 A 25-01-1990	
		JP 2781197 B2 30-07-1998	
		NL 8900757 A 16-10-1989	
		NO 175537 B 18-07-1994	
		NO 941044 A 27-12-1989	
		US 5433984 A 18-07-1995	
		US 5128410 A 07-07-1992	
		US 5229456 A 20-07-1993	
		US 5202380 A 13-04-1993	
		AU 625059 B2 02-07-1992	
		BR 8901431 A 14-11-1989	
		IL 89774 A 13-05-1993	
		IT 1232713 B 04-03-1992	
		KR 179357 B1 15-05-1999	
		NZ 228468 A 27-08-1991	
		ZA 8902168 A 26-02-1992	
		US 4997884 A 05-03-1991	
		US 5035933 A 30-07-1991	
		US 5147932 A 15-09-1992	
		US 5300570 A 05-04-1994	
JP 2276841	A	NONE	
JP 4028743	A	31-01-1992	JP 2897344 B2 31-05-1999